



CP Series End Cap

Features

- Low thermal contact impedance and buffer effect
- Good electrical insulation
- Decrease the weight of the product
- Easy to assemble


Applications

Electronic Components - 5G, Aerospace, AI, AIoT, AR/VR/MR/XR, Automotive, Consumer Devices, Datacom, Electric Vehicle, Electronic Products, Energy Storage, Industrial, Lighting Equipment, Medical, Military, Netcom, Panel, Power Electronics, Robot, Servers, Smart Home, Telecom, etc.


Standard Sizes (mm)

1. CP22 TO-220: 11.4x16x5.8
2. CP23 TO-220: 11.4x21.5x5.8
3. CP33 TO-247: 17.5x28.5x5.8

Properties



Contact Pressure, Thermal Impedance, and Deflection



Properties	Unit	CP22/CP23/CP33	Tolerance	Test Method
Thermal Conductivity	W/m·K	2.0	±10%	ASTM D5470 Modified
Thickness	mm	0.45	-	ASTM D374
Color	-	Gray	-	-
Material	-	Silicone	-	-
Operating Temperature	°C	-45~+180	-	-
Density	g/cm ³	2.55	±5%	ASTM D792
Dielectric Breakdown Voltage (AC)	kV	>10	-	ASTM D149
Dielectric Breakdown Voltage (DC)	kV	≥6	-	ASTM D149
Dielectric Constant	1000Hz	5.8	-	ASTM D150
Thermal Impedance @10psi	°C*in ² / W	1.13	-	ASTM D5470 Modified
Thermal Impedance @20psi	°C*in ² / W	1.07	-	ASTM D5470 Modified
Thermal Impedance @50psi	°C*in ² / W	0.97	-	ASTM D5470 Modified
Hardness	Shore A	65	±7	ASTM D2240

T-Global Technonology Co., Ltd.

No.33, Ln. 50, Daren Rd., Taoyuan Dist., Taoyuan City 330058, Taiwan

T +886-3-361-8899 E service@tglobalcorp.com W www.tglobalcorp.com

Version21
20260226



NOTICE: The information contained herein is to the best of our knowledge true and accurate. Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. All specifications are subject to change without notice. The protective film and release paper do not affect the function of the product. If there is no special requirement, the default depends on T-Global. Since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented with out guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology's invoice, quotation, or order acknowledgment. We disclaim any and all liabilities incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use.